

# Belcem T



## Properties

- Thixotropic premixed mortar, ready to use
- Usable for injection of self drilling-anchors, tension rods and rebars, spraying of cavities, rockface and escarpment protection, etc ...
- Composed from high resistant cements according to UNI EN 197/1
- Free of additive alkaline supplements and expansive agents

## Technical properties

Granulation	100% passing at 1.25mm
Workable time	60 – 90 minutes
Spreading acc. to UNI 7044/72	40-80%
Maturation time after 24 hours after 7 days after 28 days	> 15 N/mm <sup>2</sup> > 30 N/mm <sup>2</sup> > 45 N/mm <sup>2</sup>
Free expansion in plastic phase UNI 8996	1.5 – 2.5%
Water for mixing	22 – 24%

All above mentioned data can be subject to modifications without prior notice